

## 分散型阳离子 ED 系列

应用于阳离子可染涤纶纤维及其混纺织物的染料，提升性优异，牢度高，重现性好。

分散型阳离子 Cationic ED 系列	C.D.P	染色浓度 Dyeing depth %	耐晒 Light	热定型 Heat-t-setting	耐气蒸褶裥 Steam pleating	汗渍牢度 Perspiration			皂洗牢度 Washing CDP/羊毛	耐沸煮 (97°C) Potting/CDP/羊毛	摩擦牢度 Rubbing	
						酸性 Acid	CDP/羊毛	碱性 Alkali			干摩 Dry	湿摩 Wet
Luminous Yellow ED-10GFF 荧光黄 ED-10GFF		2.0	5	5	5	5/5	5/5	5/5	5/5	5	5	
Luminous Yellow ED-8G 荧光黄 ED-8G		2.0	5	5	5	5/5	5/5	5/5	5/5	5	5	
Yellow ED-5GL 黄 ED-5GL		2.0	5	4	4	4-5	4-5	4-5	5/5	4-5	4-5	
G.Yellow ED-GL 金黄 ED-GL		1.0	6	4-5	4-5	5/5	5/5	5/4-5	5/5	4-5	5	
Red ED-BL 红 ED-BL		1.5	4-5	5	4-5	5/5	5/5	5/5	5/5	4-5	5	
Br.Red ED-5GL 艳红 ED-5GL		2.0	3-4	3-4	3-4	5	5	4-5	5/5	3-4	3-4	
Red ED-GRL 红 ED-GRL		2.0	6↑	5	5	5/5	5/5	5/5	3-4/5	4-5	5	
Blue ED-BL 蓝 ED-BL		2.0	5-6	4-5	4-5	4	4	4-5	4/4	4-5	4-5	
Blue ED-GSL 蓝 ED-GSL		1.0	6↑	5	5	5/5	5/5	5/5	5/5	4-5	5	
Blue ED-BG 蓝 ED-BG		1.0	5-6	5	5	5/5	5/5	5/4-5	5/5	5	4-5	
Black ED-M 黑 ED-M		8.0	5-6	4-5	4-5	5/4-5	5/4-5	5/4-5	4-5/4-5	4-5	4-5	
Black ED-RN 黑 ED-RN		8.0	6	4-5	4-5	5/5	5/4-5	5/4-5	4-5/4-5	4-5	4-5	

注：1.以上牢度数据为相应深度在 CD-poly 布上所测得，供参考


First Floor, No. 58, Lane 118, Suide Road, Putuo District, Shanghai  
Tel:021-54241271 Fax:021-54241272

版本: C15 Oct 001ED



扫描全能王 创建

分散型阳离子 ED 系列染料染色推荐工艺:



注: 1.以上牢度数据为相应深度在 CD-poly 布上所测得, 供参考

First Floor ,No. 58, Lane 118, Suide Road, Putuo District, Shanghai  
Tel:021-54241271 Fax:021-54241272

版本: C15 Oct 001ED

